

FiberAcoustic® 75

Sound absorption coefficient



[To view a picture in a bigger size click here](#)

Technical data

<>

FiberAcoustic® 75	Standard	Unit	Value (MD/CD)
Weight	ISO 9864	g/m ²	65
Breaking strength	ISO 9073-18	N/5 cm	25/35
Elongation at break	ISO 9073-18	%	15/30
Thickness	ISO 9073-1	mm	0.30
Acoustic impedance		Ns/m ³	250
Fibre blend	100% FR polyester		
Length / Width	Standard 100 metres / 1200 mm		
Colour	White and black		
Flame retardancy	EN ISO 13501-1: B-s1, d0		

MD: Machine direction

CD: Cross direction

[Print this page](#)